



Phone: 0800 6444 949
 Email: info@thermal-breaks.co.uk

Product: TekTherm AK300HT

Material Specification (Typical Properties)

	Unit	Value	Test Standard
Mechanical Properties			
Flexural strength	MPa	170	ISO 178
Modulus of elasticity	MPa	10000	ISO 178
Compressive strength at 200°C	MPa	90	ISO 604
Design Compressive strength at 23°C	MPa	198	ISO 826
Friction Coefficient	/	0.15	ASTM D1894
Physical Properties			
Density	g/cm ³	1.5 (+/-0.1)	ISO 1183
Water Absorption (24h 23°C)	%	0.49	ISO 12087
Electrical Properties			
Electrical strength	kV/mm	21	IEC 60243-1
Thermal Properties			
Operating temperature*	°C	-180 +200	
Coefficient of linear expansion //	1.0E-6 / K	20	DIN 53752
Thermal conductivity*	W/m.K	0.1332	DIN 52612
Flame retardancy		V0	UL94

RoHS Directive

Hazardous products listed in the EU-directive 2011/65/EU (ROHS-directive), §4 section 1, are not used as ingredients in this material.

Benefits

- Asbestos free
- Low heat conductivity
- Excellent tolerances with respect to parallelism
- Long life expectancy > 50 years (dependent on operating conditions)
- Low water absorption
- Good hydrocarbon stability
- Good chemical stability
- Excellent mechanical durability
- Very good electrical properties
- UL 94-V0

*Manufacturers' figures

Disclaimer. These figures are typical values for the material and do not represent a product specification. Properties will vary depending on source of raw material, method of processing, physical form of product, direction of measurement etc.
 Updated 30/01/2018